



Tru-Bond™ PSA 30000

Pressure Sensitive Adhesive, UV/Visible Light Cure Adhesive

PRODUCT DESCRIPTION

Tru-Bond™ PSA 30000 is a one-part, solventless PSA (pressure sensitive adhesives) that cures to a tacky adhesive when exposed to UV/Visible light. This adhesive can be cured directly through clear or translucent surfaces or cured first prior to assembly. The curing first method allows for the joining of parts at some future point. This product can bond a wide range of substrates including PE, PP, PET, and most plastics, metals, glass, and ceramics. It can be sprayed, roll coated, bead or brush applied, screen printed or used in a flexographic printing process.

PRODUCT CHARACTERISTICS

Chemical Class	Acrylic
Appearance(uncured)	Clear liquid
Components	Single-requires no mixing
Viscosity	medium

Optical Clarity, %	>98
Water absorption, ASTM D570 (24 hrs.), %	0.4
Boiling Water, ASTM D570 (2 hrs.), %	3.4
Shore hardness	33 A
SAFT (Shear Adhesive Failure Temperature), °F(°C)	260(127)

TYPICAL PROPERTIES OF UNCURED MATERIALS

Specific gravity@23 °C	1.12
Viscosity@23 °C, Brookfield RV	
Spindle 3, 6 rpm, cP	30,000
Flashpoint, °F(°C)	>212(100)
Non-Volatile Materials, %	>99
VOC, %	<1
Shelf life, mos	24
Solubility	ketones, oxygenated solvents

ADHESION PERFORMANCE

Peel Force to Various Substrates. PSTM1 Test., 3-mil adhesive on PET film, Cured at 1.2 J/cm² with Fusion System D bulb. Assembled and then tested at 24 hours. 90° peel test.

	<u>pli</u>	<u>N/mm</u>
PVC	6.05	1.06
Acrylic	6.68	1.17
Polycarbonate	7.37	1.29
Glass	8.51	1.49
ABS	6.23	1.09
Polypropylene	4.17	0.73

TYPICAL PROPERTIES OF CURED MATERIALS

Color.	Optically Clear
Refractive Index, ASTM D542	1.48

UV CURE AND TIMELINE LATITUDE

Fusion Systems 300WPI lamp- "D"(doped) bulb at 4 inches. 3-mil PET to untreated steel

Age of uncured adhesive	Age of cured Film	Nominal Thickness (mil)	Nominal Thickness (mm)	UV Dose (J/cm ²)	30 second peel (pli)	30 second peel (N/mm)	12+ hour peel (pli)	12+ hour peel (N/mm)
2 years	2 months	0.5	0.013	0.5	3	0.525	8	1.401
2 months	2 years	0.5	0.013	1.0	1.5	0.262	8	1.401
2 years	2 months	0.5	0.013	1.5	2	0.350	8	1.401
2 years	2 months	3.0	0.076	0.5	4	0.701	8	1.401
8 months	2 days	3.0	0.076	0.8	3	0.525	11	1.926
2 months	2 days	3.0	0.076	1.5	2	0.350	11	1.926

NOTE: All of these test pieces passed >10 days of creep resistance at ambient and 50 °C.

PROCESSING

ITW products are easily applied by syringe dispense or specialty valve spray units. The materials cure extremely fast in bondlines, e.g. where the surfaces are not exposed to air, with UV or Visible radiation. Exposure doses range from .5 - 2 J/cm² depending on the intensity of the lamps and configuration of the assembly.

PRECAUTIONS

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

STORAGE

Store the unopened product in a cool, dry, well ventilated location away from sources of heat. Optimal storage temperatures should range between **10 °C (50 °F) and 32 °C (90 °F)**. **Do not expose the product to light.** It may polymerize upon prolonged exposure to ambient or artificial light. Product removed from the containers during use should not be returned to original containers in order to avoid potential contamination.

CONVERSIONS

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

WARRANTY

ITW will replace any material found to be defective. Because the storage, handling and application of this material are beyond our control, we can accept no liability for the results obtained.

NOTE

The following supersedes any provision in your company's forms, letters and papers. ITW makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW sole opinion, to justify such refund.

For technical assistance, please call: 1-800-933-8266 for NA and EU, 86-0512-63488388 for Asia

FOR INDUSTRIAL USE ONLY